


Cellular uptake and toxicity of positively and negatively charged silica nanoparticles in A549 human lung cells

Elisabeth Elje^{1,2,3}, Julia Schölermann¹, Mihaela Roxana Cimpan^{1*}, Maria Dusinska^{2*}

- 1) Biomaterials, Department of Clinical Dentistry, University of Bergen, Årstadveien 19, 5009 Bergen, Norway
- 2) NILU - Norwegian Institute for Air Research, Instituttveien 18, 2007 Kjeller, Norway
- 3) Department of Chemistry, University of Bergen, Allégaten 41, 5007 Bergen, Norway
- *) Contributed equally



Silica nanoparticles and lung cells



Aims of the study

- To identify the effect of silica nanoparticle surface charge on the cytotoxic and genotoxic effects in A549 cells.
- To identify the effect of silica nanoparticle surface charge on the cellular uptake in A549 cells.



Materials and methods

Characterization:

- **Transmission electron microscopy**
- X-ray energy dispersive spectroscopy
- **Dynamic light scattering**
- Laser Doppler velocimetry
- Nanoparticle tracking analysis


NANOPARTICLES

1 – 300 $\mu\text{g/ml}$




Raw material provided by Istituto Italiano di Tecnologia (Lecce, Italy)

A549 HUMAN LUNG CARCINOMA CELLS



+



Cytotoxicity:

- **Impedance-based cell monitoring**
- Colony forming efficiency

Genotoxicity:


- Comet assay
- Mouse lymphoma assay (L5178Y TK +/- cells)

Cellular uptake:


- **Live cell imaging**
- **Flow cytometry**

The NPs show similar characteristics

Positively charged silica NPs




Negatively charged silica NPs




The NPs show similar characteristics

Positively charged silica NPs




Negatively charged silica NPs



No detected toxicity

Cytotoxicity:


- No cytotoxic effect (by impedance-based cell monitoring, 20 $\mu\text{g}/\text{ml}$)



Genotoxicity/mutagenicity:

- no DNA damage (by the comet assay)
- no DNA oxidation (by the comet assay)
- not mutagenic (by mouse lymphoma test)

Higher uptake of positively charged silica NPs




Flow cytometry. NP concentration: 20 µg/ml

a: Statistically significant result with $P < 0.01$ relative to control cells and cells exposed to negatively charged silica NPs.


b: Statistically significant result with $P < 0.05$ relative to control cells.

Detailed uptake information from time-lapse imaging

NP concentration: 20 $\mu\text{g/ml}$
1 image/minute



A549 cells and positively charged silica NPs




A549 cells and negatively charged silica NPs


How the silica NPs move when in contact with cells

1 minute/step

Each curve represents one uptake event




Positively charged silica NPs



Negatively charged silica NPs

The distance between the NPs and the plasma membrane



Conclusions

Nanoparticles:

- Both the positively and negatively charged amorphous silica NPs were spherical, with high dispersion stability, and a hydrodynamic diameter of approximately 165 nm and 150 nm, respectively.

Toxicity:

- The silica NPs induced no significant reduction in cell viability at 20 $\mu\text{g/ml}$, and no significant DNA damage, DNA oxidation or induced mutations at 1-300 $\mu\text{g/ml}$.
- The non-cytotoxic results should be validated at additional concentrations.

Cellular uptake:

- Both positively and negatively charged NPs were internalized by the cells.
- The positively charged silica NPs were taken up faster and by more cells, compared to the negatively charged silica NPs.

Acknowledgments

- Supervisors:
Julia Schölermann, Mihaela R. Cimpan & Maria Dusinska
- Biomaterials group, University of Bergen, Norway
- Department of Chemistry, University of Bergen, Norway
- Health effects group, NILU, Norway

- Producer of NP raw material:
Istituto Italiano di Tecnologia, Lecce, Italy

Supported by NANoREG (EC FP7, 310584), NorNANoREG (Norwegian Research Council, 239199/070), the UH-Nett Vest fund and the Department of Clinical Dentistry, Faculty of Medicine and Dentistry, University of Bergen, Norway.